

Castrol Rustilo DWX 32™

De-Watering Corrosion Preventive

Description

These grades are solvent deposited water displacing type premium quality corrosion preventives. These grades offer soft waxy protective film by solvent evaporation. They have excellent water displacing characteristics and resistance to finger print corrosion. It is recommended to apply these products by immersion. However spray method can also be used for their application. The protective film can be removed by solvent, vapour degreasing or by suitable alkaline cleaners.

Application

It is recommended for severe environmental conditions and long term protection. The product is suitable for treatment prior to storage of machine tools, cam shafts, crank shafts, circular saws, large gears, exposed sliding surface lathe beds, etc. It offers good indoors and outdoors protection.

Advantages

These products offer

- ♦ Good non-staining properties
- Provides long term protection
- ♦ Easy removal
- ♠ Economy in usage

Castrol Rustilo DWX 32 26.10.2006, Version Number 1.0 "Castrol Rustilo DWX 32" and Castrol are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information included in this publication is accurate as of the date of printing. However, such information may nevertheless be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol India Limited products. MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product

Castrol India Limited, Industrial Lubricants & Services, Rayala Towers, II Tower, V Floor, 781-785, Anna Salai, Chennai – 600 002. Tel: +91 44 42198899 Fax: +91 44 28416305 Toll Free: 1800 - 425 - 4588 (BSNL) Help Line: 044-39019019 Email:customer.service@castrol.com



Product Data

Characteristics

Characteristics	Typical Value
Appearance	Hazy liquid free of insoluble particles
Specific Gravity @ 30 deg. C	0.82 to 0.83
Non-Volatile, % W/W	26 to 29
Film Thickness, Micron	4.0 (T)
Coverage M2/Ltr	60.00 (T)
Drying Time, Minutes	90 max.
Protection	Indoor - 18 months Outdoor - 9 months

These are typical figures and do not constitute a specification.

Castrol Rustilo DWX 32 26.10.2006, Version Number 1.0 "Castrol Rustilo DWX 32" and Castrol are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information included in this publication is accurate as of the date of printing. However, such information may nevertheless be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol India Limited products. MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product

Castrol India Limited, Industrial Lubricants & Services, Rayala Towers, II Tower, V Floor, 781-785, Anna Salai, Chennai – 600 002. Tel: +91 44 42198899 Fax: +91 44 28416305 Toll Free: 1800 - 425 - 4588 (BSNL) Help Line: 044-39019019 Email:customer.service@castrol.com