

PRODUCT DATA

GulfSea HYPERBAR CS2

Calcium Sulfonate Complex EP Grease for Heavy Duty Applications

Product Description

GulfSea HYPERBAR CS2 grease is heavy duty multipurpose calcium sulfonate complex soap based grease for use in a wide range of marine, industrial and automotive applications. It is manufactured from high quality solvent refined base oils and performance additives to provide good structural stability, resistance to water washout and effective protection from wear and corrosion. It is specially designed to deliver outstanding performance in severe application areas like marine, mines, offshore and heavy duty off-highway equipment.

Features & Benefits

- Outstanding extreme pressure properties extend bearing life under shock-load conditions
- Excellent mechanical stability and resistance to softening ensures long lubricant life and prevents leak out of bearings even in the presence of water
- Excellent corrosion protection and resistance to water washout resulting in improved component protection and equipment life
- Good adhesive property ensures that the grease stays in place for longer re-lubrication intervals.
- Very high drop point ensures extended operating range of up to 180°C.

Applications

- Heavy duty equipments used in marine, off-shore, cement, mining / quarrying, agriculture & forestry/ logging, off highway and other industrial as well as automotive applications under severe conditions.
- General lubrication of axles, ball joints, universal joints, couplings, power take-offs, king pins, bushings and disc brakes.

PRODUCT DATA



Typical Properties

Meets the following Specifications		
ASTM D4950 GC-LB, ISO 6743-9 L-XBFB2, DIN 51502 KP2R-25		
Typical Properties		
Test Parameters	Test Method	Typical Values
Colour	Visual	Yellow ochre
Texture	Visual	Smooth / Buttery
NLGI		2
Type of base oil		Mineral
Estimated operating temperature range		-25°C to 180°C
Base oil viscosity at 40°C; cSt	D 445	180
Consistency, worked penetration 60 strokes	D 217	280
Worked penetration after 100,000 strokes; change in consistency	D 217	3
Dropping point; °C	D 2265	305
Oil separation at 25°C for 24 hrs; %wt.	D 1742	1
Oxidation resistance, pressure drop; psi	D 942	5
Water washout at 79°C; %wt. loss	D 1264	2
Four ball weld load; kgs.	D 2596	500
Timken load; lbs	D 2509	65
SKF - EMCOR steel corrosion; rating	D 6138	0-0
Copper strip corrosion at 100°C for 24 hrs; rating	D 4048	1a
Rust protection	D 1743	Pass

October 2008



Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly.

Gulf Oil Marine Ltd

25th Floor, 3 Lockhart Road, Wan Chai, Hong Kong

Tel : (852) 3693 0568 Fax : (852) 3748 9960

Web : www.gulf-marine.com Mail : operation.hk@gulf-marine.com